


WHAT IS CLAIMED IS:


1. An aryl aminofunctional silane compound having the formula:



wherein R is an alkyl group having 1 to 6 carbon atoms; R^1 is an alkyl group having 1 to 6 carbon atoms; R^2 may be the same or different and are independently selected from alkyl groups having 1 to 6 carbon atoms; and n has a value of 0 or 1.


2. An aryl aminofunctional silane compound according to claim 1, wherein the compound is an HCl salt.

3. An aryl aminofunctional silane compound according to claim 1 wherein $\text{R}=\text{CH}_3$, $\text{R}^2=\text{CH}_3$, and $n=0$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

4. An aryl aminofunctional silane compound according to claim 1 wherein $\text{R}=\text{CH}_3$ and $\text{R}^2=\text{C}_2\text{H}_5$, and $n=0$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

5. An aryl aminofunctional silane compound according to claim 1 wherein $\text{R}=\text{C}_2\text{H}_5$, $\text{R}^2=\text{CH}_3$, and $n=0$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

6. An aryl aminofunctional silane compound according to claim1 wherein $R=C_2H_5$, $R^2=C_2H_5$, and $n=0$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

7. An aryl aminofunctional silane compound according to claim1 wherein $R=C_3H_7$, $R^2=CH_3$, and $n=0$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

8. An aryl aminofunctional silane compound according to claim1 wherein $R=C_3H_7$, $R^2=C_2H_5$, and $n=0$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

9. An aryl aminofunctional silane compound according to claim1 wherein $R=CH_3$, $R^1=CH_3$, $R^2=CH_3$, and $n=1$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

10. An aryl aminofunctional silane compound according to claim1 wherein $R=CH_3$, $R^1=CH_3$, $R^2=C_2H_5$, and $n=1$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

11. An aryl aminofunctional silane compound according to claim 1 wherein $R=C_2H_5$, $R^1=CH_3$, $R^2=CH_3$, and $n=1$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

12. An aryl aminofunctional silane compound according to claim 1 wherein $R=C_2H_5$, $R^1=CH_3$, $R^2=C_2H_5$, and $n=1$




and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

13. An aryl aminofunctional silane compound according to claim 1 wherein $R=C_3H_7$, $R^1=CH_3$, $R^2=CH_3$, and $n=1$



and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

14. An aryl aminofunctional silane compound according to claim 1 wherein $R=C_3H_7$, $R^1=CH_3$, $R^2=C_2H_5$, and $n=1$



and the HCl salt thereof, wherein methyl group is *ortho*-, *meta*-, or *para*-substituted or mixtures thereof.

15. A water-resistant substrate, comprising a glass fabric coated with at least one compound according to Claim 1.

16. A water-resistant substrate according to Claim 15, wherein the coating amount of the compound is about 0.05 to 0.2% by weight based on the weight of glass fabric.

17. A water-resistant substrate according to Claim 15, wherein the coating amount of the compound is about 0.065 to 0.15% by weight based on the weight of glass fabric.

18. A method of preparing a substrate, comprising:

applying at least one compound according to Claim 1 to a glass fabric to form a coated glass fabric; and

applying the coated fabric to an epoxy laminate thereby reinforcing the laminate.